



ALLBÄCK LINUS WALL PAINT – QUALITY CONTROL FOR HANDLING, USE AND MAINTAINCE

Allbäck Linoljeprodukter AB	Product name:	Allbäck Linus Wall Paint
Balkåkravägen 18	Binder:	Allbäck cleaned, boiled and matured linseed oil
271 91 Ystad, Sweden	Thinner:	If necessary, water approx. 10%

Area of use:

Linus White Wall Paint contains only purified cleaned boiled linseed oil, water, cellulose glue, schellac, titanium dioxide and chalk. The pigments are iron oxides and / or chromium oxide depending on the color.

The paint is solvent-free and should never be thinned with solvents.

BUILDING MATERIAL ASSESSMENT-GREEN ARROW. SUNDA HUS -A

Surface	The paint can be used on all interior surfaces: wood, painted surfaces, plaster, wallpaper, whitewash, plasterboard, woven surfaces and papered walls and ceilings. The paint is durable, resistant to stains, and easy to sand.
Application	Stir in the water on the surface. Add about 10% additional water if you wish a smoother surface. The surface varies depending on the tool and the thickness of the paint. Brush or roll with a yarn roller or spray paint (hard pressure, small nozzle).
Cleaning	Allbäck Linseed Soap. Wash hands and brushes / rollers with Allbäck Linseed Soap and water. Avoid flushing the paint down the drain.
Storage	For short-term storage of the roller, leave it in the paint or in water overnight.
Keeping	Can be stored for at least 4 years at room temperature.
Coverage	10 – 12 m ² per litre. Paint at least two coats. Highly absorbent surfaces can be pre-treated with Allbäck Primer or paint an extra coat.
Dry weight	Approx. 75 %
VOC	Less than 0,3%
Drying time	Approximately 24 hours at room temperature with good ventilation. It is possible to paint wet on wet.
Transport	No restrictions – not hazardous goods

Waste disposal

No special regulations. Let the pigments sink to the bottom. Pour off the water and throw pigment residues in the garbage. Linus left overs can be mixed with chalk or ground pumice and be used as filler.

The plastic packaging can be thrown into ordinary garbage. We have an agreement with REPA on recycling of packaging.

Technical Specification & Safety Data Sheet

These are available on our website www.allbackpaint.com

Cleaning & Maintenance

Once the colour surface has cured after a few weeks, the surface can be washed with Allbäck Linseed Soap and water. Repair painting is possible.

Comments:

The result of painting with Allbäck Linus Wall Paint depends on the surface. For highly absorbent surfaces, water damage, soot or nicotine, pre-treat with Primer.

Detailed instructions for use can be found in the Concise Handbook and short video clips on our website.
www.allbackpaint.com.

Always test surfaces for approval. In case of complaints - present your documentation and quality control.
Treated surface.....

Color type..... Day & Year.....
I / We have read the instruction manual, completed the work and painted



ALLBÄCK LINUS WALL PAINT – QUALITY CONTROL
FOR HANDLING, USE AND MAINTAINCE