

# QUALITY CONTROL - ALLBÄCK LINSEED OIL PAINT

## Binder

Allbäck cleaned, boiled and matured linseed oil

## Thinner

If necessary, Allbäck cleaned boiled linseed oil, max 5%

## Content

Cleaned boiled linseed oil and pigments. Where required, add 10-15% max 20% Allbäck pure zinc paint to all colours. The paint is solvent-free and must never be thinned with solvents.

## Surface

The paint may be used on **all clean, dry surfaces**, exterior and interior. Max. moisture content 14%. May be applied in direct sunlight. **Impregnate** dry wood and cracks with raw linseed oil before painting.

## Application

Stir the paint thoroughly. Brush roll or spray (high pressure, small nozzle).

**Cleaning**, Allbäck Linseed Soap. Wash hands and brushes with Linseed Soap and water.

## Storage

Store **brushes** suspended in raw linseed oil (never in water).

**Keeping** May be kept indefinitely, even below freezing.

## Coverage

15–20 m<sup>2</sup> per litre. Each coat should cover the surface completely and be painted in even layers. Apply the same paint in **at least three** coats on new exterior surfaces. **Thickness approximately 100 microns per coat**. Apply four coats to particularly exposed surfaces.

## Drying time

Approx. 24 hours at room temperature, ventilation, light and low humidity, 50% RH.

**Transport** No restrictions – **not** hazardous goods

Risk of self-ignition – always soak rags in water and discard!

## Waste management

No specific restrictions.

Paint remnants can be used down to the last drop. Combine any remaining paint and use as first coat or mix with about 30% water to make an emulsion for concrete floors, brick walls or wood. Tins can be discarded as normal metal waste.

## Technical specifications, safety data sheets and emission tests

These are available on our website [www.allbackpaint.com/international](http://www.allbackpaint.com/international)

**VOC <1.1% Dry matter content 100%**

## Cleaning & Maintenance

Linseed Oil Paint is elastic and thus absorbs more dirt in the initial phase. After a few years, the pigment grains start to fall out and the paint becomes “self-cleaning”.

Assuming that the surface has been given three full coats of paint, dirt and mould can be cleaned off using Allbäck Linseed Soap. Avoid too high pH. Mix the Linseed Soap with water until it foams.

Clean the surface using a sponge or a brush. Rinse thoroughly and allow to dry. When the surface turns matt and starts to become chalky, treat with Boiled Linseed Oil or Linseed Oil Wax or a coat of

Linseed Oil Paint. The need for maintenance varies considerably depending on the original treatment, exposure to the elements and other stresses. Interior surfaces have much longer maintenance intervals and retain their shine for many years.

Touch-up work will have a different shine initially.

**Comments:**

The results of applying Allbäck Linseed Oil Paint depend on the structure, surface, preparation, temperature, humidity, ventilation, light and method of application. **Detailed instructions** and videos can be found in the **Little Handbook** on our website [www.allbackpaint.com/international](http://www.allbackpaint.com/international).

**Always paint a test area first.** In the event of a complaint, please include your documentation.

Treated surface .....  
With type of paint .....  
Weather .....  
Date.....

I/We have read the instructions and made the work

Name

---